

Spring-Summer 2020 - "Neutral Waves" Eyeshadow Pen with SanSilica 307



Phase	Trade Name	INCI Name	Supplier	Formula #
				210-76
A	NOO Crystal	Octyldodecyl Oleate, Tocopheryl Acetate	Sandream Impact	12.70
	Jarcol I-20 CG	Octyldodecanol	Jarchem	12.50
	SanSilica 307	Silica	Sandream Impact	1.00
	Jeesilc PTMF	Phenyltrimethicone	Jeen	10.00
	Softsan 649	Bis-diglyceryl Polyacyladipate	Cremer	6.00
	Snow White Petrolatum	Petrolatum	Penreco	6.00
	Jeenate 3H	Polyethylene	Jeen	5.00
	Beeswax SP-422P	White Beeswax	Strahl and Pitsch	5.50
	Carnauba SP63	Copernicia Cerifera	Strahl and Pitsch	4.80
	Candellilla SP75	Euphorbia Cerifera	Strahl and Pitsch	3.00
	Paraffin SP227B	Paraffin	Strahl and Pitsch	2.00
	Vitamin E	Tocopheryl Acetate	Sandream Impact	1.50
B	Fiesta Lemon Yellow	Synthetic Fluorphlogopite, Titanium Dioxide, Aluminum Oxide, Iron Oxides, Tin Oxide, Triethoxycaprylylsilane	Sandream Impact	10.00
	Glamour Rainbow Saffron	Al. Ca. Na. Silicate. TiO2, SnO2, Yellow 5	Sandream Impact	10.00
C	Purolan IDD	Isododecane	Lanxess	10.00
TOTAL PERCENT				100.00

Procedure: Weigh all of phase A into glass beaker and heat to 90°C. Mix with propeller and continue mixing until all raws are dissolved and solution is homogenous. Add phase B and slowly mix until uniform. Lower temperature to 80° and slowly add phase C. Cover and mix until uniform, pour into molds, freeze for 10 minutes for easy release.

The information provided is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Sandream Impact LLC. Customers should utilize formulations provided as a guide and perform in-house stability, micro and other necessary testing.



sandream
specialties

A VIVIFY COMPANY

373 U.S. 46 Building E
Fairfield NJ 07004 USA

+1 973.882.3077
sandreamspecialties.com
info@sandreamspecialties.com